



# Nafion™ NE326

## Ion Exchange Materials

## Product Information

Nafion™ NE326 is a highly selective perfluorosulfonic acid (PFSA) cation exchange membrane, combining outstanding chemical resistance with a strong polytetrafluoroethylene (PTFE) fiber reinforcement. It may be used for a variety of specialty electrolytic processes with low electrolyte concentration, including electroplating applications and production of quaternary ammonium hydroxides and sodium hypochlorite (NaOCl).

### Performance

Laboratory Cell (45cm<sup>2</sup> active area)\*

Membrane Type	Cell Voltage, V	Current Efficiency, %	NaOH, %
Nafion™ NE326	3.53	88	10-14

\* Conditions: 3 mm gap, 0.0045 m<sup>2</sup>, DSA anode, activated nickel cathode, 200 g/L anolyte, 90°C (194°F), 4.0 kA/m<sup>2</sup>

### Comparative Physical Attributes

Membrane Type	Tensile Strength, Kg/cm width	Linear Expansion in water, Dry to Wet 25°C	PTFE Reinforcement
Nafion™ NE326	7	4.5%	Yes
Nafion™ N424	7	6.5%	Yes
Nafion™ N115	2	10%	No

### Form

Nafion™ NE326 is shipped in the dry H<sup>+</sup> form. Dry H<sup>+</sup> membranes typically require simple pretreatment in corresponding electrolyte composition.

**Note:** The side marked CATH is intended to be installed facing the cathode for optimal performance in most cases.

### Size and Packaging

Nafion™ membranes are available in custom sizes with widths up to 1.29 meters and lengths up to 2.5 meters. Nafion™ NE326 membrane is shipped dry. Small sheets are sealed in pouches and shipped flat in wooden containers. Large sheets are rolled on polyethylene covered fiberboard or plastic tubes, overwrapped with polyethylene sheeting, and shipped in a plastic container.

### Order Information

The size availability of this product may vary; please contact your local representative for Nafion™ products.

The data listed here fall within the normal range of product properties, but they should not be used to establish specification limits nor used alone as the basis of design. This information is based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. This information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no obligation or liability in connection with any use of this information or for results obtained in reliance thereon. The disclosure of the information is not a license to operate under or a recommendation to infringe any patent of Chemours or others.

**Medical Statement:** Please contact your Chemours representative to discuss limitations regarding medical applications.

For more information about Nafion™, contact:

The Chemours Company FC, LLC  
Global Customer Service for IXM  
22828 NC Highway 87 W  
Fayetteville, NC 28306, USA

Telephone USA: (800) 283-2493  
Fax: (302) 861-3736  
Email: [customerservice.nafion@chemours.com](mailto:customerservice.nafion@chemours.com)  
Web: [chemours.com/Nafion](http://chemours.com/Nafion)

© 2024 The Chemours Company FC, LLC. Nafion™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company. C-11976 (11/24)